

## SPECIFICATION

**NAME:** KR-19SH RMA Sn62 Ag2 P2 Cored Solder Wire

Lot No.	Type
	KR-19SH RMA Sn62 Ag2 P2 Flux Content P2 (1.6-2.6%) Dia(mm): 0.3, 0.38, 0.5, 0.65, 0.8, 1.0, 1.2, 1.6

### **Nihon Almit Co. Ltd.**

- Head Office:** Almit Bldg., 2-14-2 Yayoicho, Nakano-ku, Tokyo, 164  
Japan, Tel: +81 3-3379-2277, Fax: +81 3-3374-2593
- Osaka Office:** Ashiike Bldg. No. 2, 3-6-28, Minamisenba, Chuo-ku, Osaka,  
542 Japan, Tel: +81 6-252-5039, Fax: +81 6-252-5026
- Kyushu Office:** Fukuoka D Bldg., 2-12-26, Hakataekimae, Hakata-ku,  
Fukuoka, 812 Japan,  
Tel: 092-483-0367 Fax: 092-483-0324
- Chubu Almit:** Meisho Bldg. 8F, 4-1-3, Ohsu, Naka-ku, Nagoya, 460 Kogyo,  
Japan, Tel: +81 52-241-1171, Fax: +81 52-241-2426
- Almit GmbH:** Dekan-Groh-Strasse 4, D-64720 Michelstadt/ near Frankfurt,  
Germany  
Tel.: +49 6066 969 100, Fax: +49 6066 969 102

1. **Product Name** : KR-19SH RMA Sn62 Ag2 P2

2. **Scope** : This spec. is specified for the Almit KR-19SH RMA Sn62 Ag2 P2 delivered by Nihon Almit Co., Ltd. to Company \_\_\_\_\_ .

3. **Dimension** : Mass & allowances are as followings.

Dia (mm)								Weight of one reel (Kg. NET)		
0.3	0.38	0.5	0.65	0.8	1.0	1.2	1.6	0.5	0.8	1.0
±0.05								+0.01 -0		

4. **Physical Properties** :

Solidus	Liquidus	Specific Gravity
179°	182°	8.4

5. **Characteristics** :

Items	Characteristics	Test Methods
Solids Content, Flux (%)	P2 (1.6–2.6%)	IPC-TM-650:2.3.34
Copper Mirror Test	Pass	IPC-TM-650:2.3.32
Silver Chromate	Pass	IPC-TM-650:2.3.33
Corrosion Test	Pass	IPC-TM-650:2.6.15
SIR (85%, 85%, 168hr, measured out of Chamber) (Ω)	≥ 1×10 <sup>9</sup>	IPC-TM-650:2.6.3.3
Quantitative Halide	L 1	IPC-TM-650:2.3.35
Flux materials composition	RE	J-STD-004:1.2

6. **Chemical Composition (%)** :

Composition	Principal Component			Impurities					
	Sn	Pb	Ag	Sb	Cu	Bi	Zn	Fe	Al
Standards	62.0 ±0.5	Rest	2.0 ±0.3	≤0.50	≤0.080	≤0.10	≤0.005	≤0.020	≤0.005
Composition	Impurities								
	As	Cd	Au	In	Ni	P	S		
Standards	≤0.030	≤0.005	≤0.080	≤0.10	≤0.010	≤0.010	≤0.005		

**7. Lot size :** A lot contains 500kg which is the amount of a single melting.

**8. Packing :**

Individual Package		Outer Package	
Unit	Packing	Unit	Packing
0.5, 0.8, 1.0 kg	Plastic Bag	5, 8, 10 kg	Cardboard

**9. Identification :**

Unit		Cardboard	
Name	KR-19SH RMA Sn62 Ag2 P2	Name	KR-19SH RMA Sn62 Ag2 P2
Sn Content	Sn62	Sn Content	Sn62
Flux Content	P2 (1.6-2.6%)	Flux Content	P2 (1.6-2.6%)
Diameter	mm	Diameter	mm
Weight	(EX. net 500g)	Weight	(EX. net 5 kg)
Lot No.	(EX. 03.2.3)	Lot No.	(EX. 03.2.3)
Maker	Nihon Almit Co., Ltd.	Maker	Nihon Almit Co., Ltd.

**12. Maker Address:** Nihon Almit Co., Ltd., Almit Bldg., 2-14-2 Yayoicho, Nakano-ku, Tokyo, 164, Japan

**13.** In case of changing this spec., it must be accepted by

**14.** This product is manufactured, using all guaranteed materials according to the "LAW ON INSPECTION AND MANUFACTURING OF CHEMICAL SUBSTANCES".

**15.** The basic quality of solder and flux of this product conforms to Federal Spec. QQ-S-571F.

**16. Shelf life:**

Up to two (2) years from the manufactured date (Lot number).