

SPECIFICATION

NAME : Almit SRC Solder Paste
LFM-14W TM-HP

Item No.	Type
	LFM-14W TM-HP Flux Content 12,0% Solder Powder Size: 20-38 (µm)

NIHON ALMIT CO., LTD

Head Office: Almit Bldg., 2-14-2, Yayoicho, Nakano-ku, Tokyo 164 Japan
Tel: +81 3-3379-2277, Fax: +81 3-3374-2593

Productive Engineering Center: 8154-227, Uenohara, Kitatsuru-gun, Yamanashi 409-0112 Japan
Tel: +81 554-62-2281, Fax: +81 554-62-2282

Osaka Office: Ashiike Bldg., 3-6-5, Minamisenba, Chuo-ku, Osaka 542, Japan
Tel: +81 6-252-5039, Fax: +81 6-252-5026

Kyushu Office: Pacific Atlas Fukuoka Bldg., 2-12-26, Hakataekimae, Hakata-ku, Fukuoka-shi 812 Japan.
Tel: +81 92-483-0367, Fax: +81 92-483-032

Chubu Almit Kogyo: Daiwa Bldg., 4-2-58, Ohsu, Naka-ku, Nagoya-shi 460, Japan
Tel: +81 52-241-1171, Fax: +81 52-241-2426

Almit GmbH: Dekan-Groh-Strasse 4, D- 64720 Michelstadt/near Frankfurt, Germany
Tel.: +49 6066 969 100, Fax: +49 6066 969 102

1. Product Name : LFM-14W TM-HP

2. Scope : This spec. is specified for Almit solder paste LFM-14W TM-HP delivered by Nihon Almit Co., Ltd. to Messrs. _____ .

3. Weight & Allowances: (g)

Weight	500
Allowance	-0, +10

4. Chemical Composition : (wt%)

Comp.	Main Constituents							
	Sn	Ag	Cu					
Standard	Bal	3.5±0.2	0.7±0.1					
Comp.	Impurities							
	Pb	Sb	Bi	Zn	Fe	Al	As	Cd
Standard	≤0.09	≤0.12	≤0.10	≤0.002	≤0.02	≤0.002	≤0.03	≤0.002

5. Solder Powder Size & Distribution (J-STD-005 3.3.2)
% of Sample by Weight – Nominal Size

Type	None Larger Than	Less Than 1% Larger than	80% Minimum Between	10% Maximum Less Than
Type4	40 Microns	38 Microns	38-20 Microns	20 Microns

6. Characteristics :

Characteristics	Standard	Test Methods
Metal Percent (wt%)	88.0±1.0	IPC-TM-650 2.2.20
Silver Chromate	Pass	IPC-TM-650 2.3.33
Copper Mirror Test	Pass	IPC-TM-650 2.3.32
SIR (85°C, 85%, 168 hr, measured out of chamber) (Ω)	≥1×10 ⁸	IPC-TM-650 2.6.3.3
Corrosion Test	Pass	IPC-TM-650 2.6.15
Flux materials composition	RO	J-STD-004 1.2
Quantitative Halide	L1<0.5%	IPC-TM-650 2.3.35
Fluorides By Spot Test	Pass	IPC-TM-650 2.6.35.1

7. Physical Properties:

Metal Name	Solidus (°C)	Liquidus (°C)	Specific Gravity
LFM-14	217	218	7.4

8. Lot Size :

A single lot is consisted of, and may vary between 10 - 100kg, depends upon the production plan.

9. Quality and Inspection :

Inspection items are applied to each lot as follows:

Item No.	Inspection Item	Contents	Standard
1	Appearance	Colour	Comparison with Limit Specimen
2	Weight	Net Weight	-0, +10 (g)
3	Solder Powder Size	20-38 (W)	94≤ (wt%)
4	Metal Composition	Sn	Balance (wt%)
		Ag	3.5±0.2 (wt%)
		Cu	0.7±0.1 (wt%)
5	Characteristics	Flux Content	12.0±0.5 (wt%)
6		Solder Balling Test (*Almit Method)	Comparison with Limit specimen
7		Viscosity (Spiral type, 10rpm, 25°C) (IPC-650-2.4.34.3)	200000±30000 (cps) 200±30 (Pa·s)
8		Solderability on Cu Plate	Comparison with Limit Specimen
9		Dryness	Chalk powder should be easily removed from each test specimen.

*Straight lines of solder paste are printed on to a JIS-2 type substrate then reflowed. The reflowed solder is examined with a stereo microscope at 30X magnification. No more than 2 solder balls larger than one fifth the size of the pattern gap is allowed per gap.

10. Packing :

Individual Packaging		Outer Packaging	
Unit	Packaging	Unit	Packaging
500 g	Polyethylene bottle with inner lid	10.0 Kg 20.0 Kg	Cardboard box

11. Identification :

	Polyethylene Bottle	Cardboard Box
Name	Almit SRC Solder Paste LFM-14W TM-HP	Same as the left
Lot No.	(Ex.) 0301007-1	Ditto
Solder Powder Size	20-38 μ m	Ditto
Date of Mfg.	(Ex.) 03-10-7 (Indicate in the Christian era)	Ditto
Weight (Net)	(Ex.) 500 g	Ditto
Company Name	NIHON ALMIT CO., LTD.	Ditto

12. Maker Address :

Nihon Almit Co., Ltd.

Almit Bldg., 2-14-2 Yayoicho, Nakano-ku, Tokyo, Japan

13. In case of **changing this spec.**, it should be accepted by _____ .

HOW TO HANDLE LFM-14W TM-HP

1. Storage:

- Hold in a refrigerator. (0-10°C)
- It is recommended to use within 6 months from manufacturing date.
- The solder paste should be used as quickly as possible once lid has been opened.
- Unused solder paste in the jar should be refrigerated after re-applying the inner and outer lids.

2. How to Use:

- Prior to usage, solder paste should be removed from refrigeration for over 2 hours until it reaches room temperature.
- We recommend to stir the solder paste by mixing machine before use it. When stir by a spatula, open the jar after the solder paste is warmed up to room temperature and stir slowly to make the paste homogeneous. Caution must be taken not to mix in air.
- After printing the solder paste, mount components immediately and let it pass through reflow furnace.
- We recommend to use N₂ reflow furnace.
- Slowly heat the reflow furnace at 1.0 to 2.0°C/second till reaching 120°C. Set peak temperature at 170 to 190°C during pre-heating and 230 to 250°C during reflow.
- This solder paste corresponds to No-Clean process, however confirmation may be required whether No-Clean process is applicable under user's expectancy.
- White residue (insulator) may appear after cleaning.
- Solder paste must be wiped off from metal mask, squeegee and spatula by applying solvent such as alcohol immediately after use.

3. Caution:

- The solder paste is not edible.
- The solder paste is for the industrial use only.
- Avoid contact with eyes and skin.
- Avoid inhalation of gases emitted by solder paste during use.
- Provide proper ventilation.

4. Notice:

- If contact with skin, wiped off with like alcohol and wash with soap and water, immediately.
- Use rubber gloves and protective glasses, if necessary.

5. Delivery:

- Usually 2-3 weeks from acceptance of order.